



StaBrite is an excellent, low maintenance coating with outstanding resistance to scuffs, scratches, black heel marks and detergent scrubbing.

DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 5-6 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 4 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

PRODUCT INFO

Product Code 130MPE

Volume 4 liters

Shipping Package 4 x 4
liters

Pallet Quantity 48

SURFACES



VCT

TECHNICAL DATA

Description	Polymer emulsion
Appearance	Milky white
Specular Gloss (60°) ASTM D1455-87 (2008)	>85
Viscosity (Brookfield) @ 68°F (20°C)	<10 centipoise
Coverage Rate	2500 to 3000 ft ² /gal 61 to 74 m ² /liter
Dry Time	About 30 minutes
Removability ASTM D1792-06	Excellent
VOC 40 CFR Part 59 Subpart C	0.02%
Total Solids	26%
Non-Volatile Solids ASTM D2834-95 (2008)	20%
Odor	Slight ammoniacal
Slip Resistance ULTM410	Meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-98 (2008)	8.6 lb/gal @ 68°F 1.03 kg/L @ 20°C
Detergent Resistance ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles
Container	2.5 US gal/9.5 L (FS packaging) 2.64 US gal/10 L (FSE packaging) 1.06 US gal/4 L (MPE packaging) 55 US gal/208 L (DR packaging)



Floor Coating and Finishing materials
as to slip resistance only. 42E6